

1- Part Industrial / Construction Grade Silicone Sealant

Technical Data Sheet

MULTI-SURFACE 1-PART INDUSTRIAL/CONSTRUCTION GRADE SILICONE SEALANT

Brick It is a one component, low modulus, neutral cure silicone sealant and adhesive created to bond a wide variety of building materials. When fully cured, this unique VOC compliant formula offers UV stability and tenacious adhesion to pvc, concrete, glass, aluminum, painted surfaces, wood, plywood, stucco, building paper, window wrap, fiber cement, brick, stone, steel, ceramic, porcelain, masonry, plus many other common material surfaces. This product is specifically formulated to offer all weather performance to meet today's Green Building Standards.

FEATURES & BENEFITS

- Multi-Surface
- Excellent Adhesion
- Non-Corrosive
- Low Odor
- 50% Movement Capability
- Permanent Flexibility
- Excellent Weatherability
- Long Life
- VOC Compliant
- Non-Flammable
- Waterproof

CONSTRUCTION & INDUSTRIAL APPLICATIONS

- | | |
|---|--|
| <ul style="list-style-type: none"> Sealing Openings & Exterior Surfaces HVAC/R Plumbing Roofing Kitchen & Bath Countertops Sanitary Seals | <ul style="list-style-type: none"> Precast Concrete Industrial Gaskets Transportation Seals Marine Cabins Appliance Trim & Parts Interior/Exterior Above Grade |
|---|--|

MEETS SPECIFICATIONS: ASTM C920 Type S, NS, Class 50, TT-S-00230C, TT-S-01543A, MIL-A-46106A, AAMA 808.3, 805.2, 803.3 (Type I), 802.3 (Type II); UL Recognized Component.

PHYSICAL PROPERTIES		TEST METHOD
Cure System	Neutral/Oxime	
Movement Capability, %	±50%	ASTM C-719
Modulus	Low	ASTM D-412
Physical Properties (Cured)	Rubber	
Specific Gravity	1.04	
Extrusion Rate, g/min.	500	ASTM C-1183
1/8" orifice @ 50 psi		Modified
Temperature Range	-62°F to 400°F	
Intermittent Temperature Range	450°F	
Accelerated Weathering (10,000 hrs.)	No Change	QUV Weatherometer
Skin Over Time (min)	12*	MNA Method
Tack Over Time (min)	25*	ASTM C-679
Cure Rate	1/8" per 30hrs*	MNA Method
Tensile Strength (psi)	190	ASTM D-412
Elongation %	650	ASTM D-412
Durometer Shore A	15	ASTM C-661
Dielectric Strength kv/mm (v/mil)	20 (500)	
Dielectric Constant at 100 Hz	2.7 @ 96	
Shelf Life (months)	18	
Volatile Organic Content	40 gr./litre	

*All properties derived from lab conditions (77° F at 50% relative humidity)

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

