























Technical Data Sheet

Craftsman Series
York Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Antique Ivory		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Atlanta		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Avignon		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Barlow		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Belgium		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Brandywine		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Cherry Lane		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Donohue		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
French Provincial		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Georgian		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Lorraine Full Range		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Monticello		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Old Savannah		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Rockdale		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Rose Full Range		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Royal Essex		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Sahara		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Scotch Tradition		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Shenandoah		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Trevanion		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Victorian		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Virginia Blend		Oversize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Handmade Oversize	4"	2-3/4"	8-1/2"	6.4	385	5.2























Note: products are also available as Thin Brick, see Thin Brick Technical Data Sheet.

Technical Data Sheet

Craftsman Series -- Thin Brick

York Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Antique Ivory Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Atlanta Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Avignon Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Barlow Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Belgium Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Brandywine Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Cherry Lane Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Donohue Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
French Provincial Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Georgian Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Lorraine Full Range Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Monticello Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Old Savannah Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Rockdale Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Rose Full Range Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Royal Essex Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Sahara Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Scotch Tradition Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Shenandoah Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Trevanion Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Victorian Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Virginia Blend Thin Brick		Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Thickness	Width	Height	Length	Weight	Brick per Pack	Brick per Sq Ft
HMO5 Thin Brick Flat	1"	1"	2-3/4"	8-1/2"	1.7	22	5.2
HMO5 Thin Brick Corner	1"	4"	2-3/4"	8-1/2"	2.2	8	3.7/LF

Note: products are also available as Full Brick, see Full Brick Technical Data Sheet.